

## TEST REPORT

Page 1 of 3

ULR - TC65282600004481F

Report No.: M2605210001

Date: 25-05-2026

Issued To:

**M/s SKYDECOR LAMINATES PVT. LTD.**

PLOT NO. - 136, ECOTECH I EXTN., GREATER NOIDA - 201310

Sample Description : SKYDECOR SDL 30303 SF  
Sample Received Date : 21-05-2026  
Sample Drawn By : Client  
Specification : --  
Test Requested : FLAMMABILITY, Food Grade  
Test Method : Refer to Attached Pages.  
Test Result : Refer to Attached Pages.

### SAMPLE PICTURE



Authentication: To Check authenticity of Test report (s). Scan QR code to get original data.



**BIS, DGQA & Various Govt. Approved Laboratory**  
**ISO 9001:2015, ISO 14001:2015 & ISO 45001 :2018 Certified Laboratory**

#### Terms & Conditions

1. Sample will not be retained more than one month for chemical and three months for mechanical unless specified instructed. 2. Samples analysis conducted on as received basis and followed by customer description, unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. The statement of conformity furnished herewith based on decision rule AAL/DRCS of our laboratory 5. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 6 The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 7. Total liability of our laboratory is limited to the invoiced amount only. 8. This report cannot be used as and evidence in a court of law without the written approval of the laboratory.

AAL/MSF/QA/52





## TEST REPORT

ULR - TC652826000004481F

Report No.: M2605210001

Date: 25-05-2026

### I. Chemical

#### Food Grade Test

Test performed on : 21-05-2026 to 25-05-2026

#### OVERALL MIGRATION TEST REPORT

TEST	TIME	TEMP.	MAX. PERMISSIBLE LIMITS	MDL	RESULT (mg/dm <sup>2</sup> )
<b>OVERALL MIGRATION</b>					
<b>SIMULANTS USED</b>					
3% Acetic acid (W/V) aqueous solution	2.0 hrs.	70°C	<10 mg/dm <sup>2</sup>	3.0	4.2
50% Ethanol (V/V) aqueous solution	2.0 hrs.	70°C	<10 mg/dm <sup>2</sup>	3.0	ND
10% Ethanol (V/V) aqueous solution	2.0 hrs.	70°C	<10 mg/dm <sup>2</sup>	3.0	ND
Rectified olive oil	2.0 hrs.	70°C	<10 mg/dm <sup>2</sup>	3.0	ND
n-Heptane	0.5 hrs.	38°C	<10 mg/dm <sup>2</sup>	3.0	ND
<b>Colour Migration</b>	---	---	No Colour	No colour observed	
<b>HEAVY METAL IN COLORANTS (N/10 HCL SOLUTION)</b>					
Barium	--	--	1 mg/kg	0.3	ND
Cobalt	--	--	0.05 mg/kg	0.01	ND
Copper	--	--	5 mg/kg	0.5	ND
Iron	--	--	48 mg/kg	0.3	5.2
Lithium	--	--	0.6 mg/kg	0.2	ND
Manganese	--	--	0.6 mg/kg	0.3	ND
Zinc	--	--	25 mg/kg	0.5	4.8
Aluminium	--	--	1 mg/kg	0.1	ND

**Note:** 1. M.D.L. = Method detection limit      2. N.D.= Not detected

3. mg/dm<sup>2</sup> = milligram per square decimetre


4. Analytical tolerance of aqueous simulants is 1mg/dm<sup>2</sup> or 6mg/kg.

5. Analytical tolerance of fatty food simulants is 3mg/dm<sup>2</sup> or 20mg/kg.

6. Permissible limits is accordance with reference to Commission regulation (EU) No. 10/2011 of 14 Jan 2011 with amendments.

**Test method:** IS:9845-1998 ,EN 1186-9:2002 and EN 13130-1:2004

Authentication: To Check authenticity of Test report (s). Scan QR code to get original data.



#### Terms & Conditions

1. Sample will not be retained more than one month for chemical and three months for mechanical unless specified instructed. 2. Samples analysis conducted on as received basis and followed by customer description, unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. The statement of conformity furnished herewith based on decision rule AAL/DRCS of our laboratory 5. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 6 The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 7. Total liability of our laboratory is limited to the invoiced amount only. 8. This report cannot be used as and evidence in a court of law without the written approval of the laboratory.





## TEST REPORT

ULR - TC652826000004481F

Report No.: M2605210001

Date: 25-05-2026

### II Mechanical

#### 1. Flammability Test

Test performed on : 21-05-2026 to 25-05-2026

#### FLAMMABILITY TEST

**Lab Environmental Condition:**

Ambient Temperature

23 ±2°C

Relative Humidity

50 ±5 %

**Test Method:** (UL94-2021)

Test for flammability of plastic & rubber materials for parts in devices and appliances.

**Test Conditioning:** Five specimens were conditioned for 48 hours at temp.23±2°C and relative humidity 50±5%.

**Flame Applied:** Apply the test flame for 10 ±1 seconds without changing its position.

**Test Specimen Size:** 125.0 X 12.7 X 1.0 mm

Criteria condition	Specimen & Observation					Requirement		
	1	2	3	4	5	V-0	V-1	V-2
Thickness (mm)	1.0	0.99	0.98	1.01	1.02	-	-	-
After flame time for each individual specimen t1(sec)	3	4	3	3	5	≤10	≤30	≤30
After flame time for each individual specimen t2(sec)	4	5	4	5	5	≤10	≤30	≤30
Total after flame time (sec) t1 plus t2 for the 5 specimen	41					≤50	≤250	≤250
After flame plus afterglow time for each individual specimen after the second flame application (t2+t3 sec)	7	9	7	8	10	≤30	≤60	≤250
After flame or afterglow of any specimen up to the holding clamp	No	No	No	No	No	NO	NO	NO
Cotton indicator ignited by flaming particles or drops	No	No	No	No	No	NO	NO	YES

**Test Result:** The result are complies with the V-0 requirement of UL 94 vertical burring test .

Authentication: To Check authenticity of Test report (s). Scan QR code to get original data.



Chetan  
SR. ANALYST

Reviewed and Authorized By

-----End of Report-----

BIS, DGQA & Various Govt. Approved Laboratory  
ISO 9001:2015, ISO 14001:2015 & ISO 45001 :2018 Certified Laboratory

**Terms & Conditions**

1. Sample will not be retained more than one month for chemical and three months for mechanical unless specified instructed. 2. Samples analysis conducted on as received basis and followed by customer description, unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. The statement of conformity furnished herewith based on decision rule AAL/DRCS of our laboratory 5. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 6 The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 7. Total liability of our laboratory is limited to the invoiced amount only. 8. This report cannot be used as and evidence in a court of law without the written approval of the laboratory.

AAL/MSF/QA/52

